

1. Composition

Au + Pt group-metals	78.90%
Au	75.90%
Ag	10.20%
Cu	5.90%
Zn	5.00%
Pt	2.90%
Ir	0.10%

2. Physical Properties

Melting range	840-880°C
Colour	yellow

3. Mechanical Properties

Requirements by ISO 9333 :2006

Rm > 250 Mpa or > 0.2% proof stress of the weakest of the parts

Corrosion: no visible reaction on the surface of the brazed and tested sample

4. Certification

The solder corresponds to the standard ISO 9333.

Manufacture, packing and delivery are constantly monitored according to the quality management system standards according to ISO 9001 and ISO 13485.

Cendres+ Métaux SA



Dr. Carmen Krüger
Head of Materials Development



Dr. Flavio Campana
Head of Material Testing